Dr. H. Wakeham (2) January 30, 1964

Frank E. Resnik ✓

Reconstituted Tobaccos in Competitive Brands

re: Memo on Reconstituted Tobaccos in Competitive Brands, F. E. Resnik to H. Wakeham dated 12-31-63.

Memo on Reconstituted Tobaccos in Competitive Brands, H. Cullman to H. Wakeham dated 1-2-64.

Memo on Reconstituted Tobaccos in Competitive Brands, F. E. Resnik to H. Wakeham dated 1-10-64.

The addendum report covering the TFP product obtained from the HTI sample* was prepared by Mrs. V. Johnson and is attached for your information. The TFP material is very similar to the Schweitzer paper-made reconstituted tobacco based on microscopic examination and disintegration in water. The TFP material disintegrates in water more quickly than does the Reynolds Tobacco Company material. The TFP material disintegrated in about 40 minutes whereas the Reynolds material was still intact after three hours of agitation.

The wood fiber content of L & M reconstituted tobacco is approximately 24%.

* HTI sample #324, TFP, 1711 Commander with flavored TFP. F. E. Resnik

FER:rab

cc: Dr. R. B. Seligman
Mr. H. B. Merritt

PM3000985724

Source: https://www.industrydocuments.ucsf.edu/docs/htlk0001